

**MAZZONETTO Spa**

Via A. Ceccon, 10 - 35010 Loreggia (PD)

t. +39 049 9322611 - f. +39 049 9322650

mazzonetto@mazzonettometalli.it

www.mazzonettometalli.it

**prepainted aluminum VESTIS / SURFACES**

Reference standard:	
UNI EN 1396, UNI EN 573-3, UNI EN 485, UNI EN 13523, UNI EN 13501	
Technical features:	
Base metal	Aluminium 99,5%
Alloy type	Alloy series 3000
Temper	H41
FRONT SIDE coating	35 µm K2 surface (+/- 3 µm)
BACK SIDE coating	25 µm super-polyester
Colors	Copper Roof - Green Roof - Grey Roof - Testa di Moro RAL 7016 - RAL 9006 - RAL 7037 - RAL 9002 - Black Grafite - Agate Grey - Slate Grey - Quartz Grey
Brilliance	- Copper Roof - Green Roof - Grey Roof: 15 GU - Testa di Moro RAL 7016 - RAL 9006 - RAL 7037 - RAL 9002: 30 GU - Black Grafite - Agate Grey - Slate Grey - Quartz Grey: 5 GU
Reaction to fire classification	A1
Chemical composition:	
Manganese (Mn)	1,0 - 1,5 %
Magnesium (Mg)	0,2 - 0,6 %
Iron (Fe)	0,7 %
Silicon (Si)	0,6 %
Mechanical properties:	
Tensile strength	130 - 180 Mpa
Elongation	8,00 % min.
Cracking resistance in bending (bend testing)	≤ 1,5 T
Coating adhesion	≤ 1,0 T
Surface hardness "pencil"	H
Corrosion Resistance	hours salt spray test: 1500 h
UV resistance	Test QUV 2000 h Class of UV resistance: RUV4
Dimensional characteristics:	
Standard thickness	0.70 mm
Standard widths	500 mm - 650 mm - 1300 mm
Coil weight	from 50 to 3000 kg
Applications:	
Profiling, bending, calendering according to UNI EN 612	
Use:	
Civil and industrial building industry	



vestis

prepainted aluminum VESTIS / 3D SURFACES

Reference standard:	
UNI EN 1396, UNI EN 573-3, UNI EN 485, UNI EN 13523, UNI EN 13501	
Technical features:	
Base metal	Aluminium 99,5%
Alloy type	Alloy series 3000
Temper	H44
FRONT SIDE coating	35 µm 3D surface (+/- 3 µm)
BACK SIDE coating	25 µm super-polyester
Colors	Grigio Dolomiti – Ral 7016 – Ral 7037 - Cortex
Brilliance	Grigio Dolomiti – Ral 7016 – Ral 7037 - Cortex: 5 GU
Reaction to fire classification	A1
Chemical composition:	
Manganese (Mn)	1,0 – 1,5 %
Magnesium (Mg)	0,2 – 0,6 %
Iron (Fe)	0,7 %
Silicon (Si)	0,6 %
Mechanical properties:	
Tensile strength	130 – 180 Mpa
Elongation	3,00 % min.
Cracking resistance in bending (bend testing)	≤ 1,5 T
Coating adhesion	≤ 1,0 T
Surface hardness "pencil"	H
Corrosion Resistance	salt spray test: 1500 h
UV resistance	Test QUV 2000 h Class of UV resistance: RUV4
Dimensional characteristics:	
Standard thickness	Grigio Dolomiti: 1000X0,80 – 1250X0,80 – 1000X1,00 – 1250X1,00 Ral 7016: 1000X0,80 – 1250X0,80 Ral 7037: 1000X0,80 – 1250X0,80 – 1000X1,00 Cortex: 1000X0,80 – 1250X0,80 – 1000X1,00 – 1250X1,00
Standard widths	1000 mm – 1250 mm - All widths on request
Coil weight	from 50 to 3000 kg
Applications:	
Profiling, bending, calendering according to UNI EN 612	
Use:	
Civil and industrial building industry	